

ESPRENE SPO V0115

Ethylene - Propylene - copolymer

Main Properties	Unit	Typical Value								
Mooney Viscosity ML 1+4(100°C)	MU	12								
Ethylene Content	(%)	77								
Density	kg/cm ³	869								
SSI※		18.0								
Pour Point※	°C	-25								
<table border="1"> <thead> <tr> <th colspan="2">※Formulation</th> </tr> </thead> <tbody> <tr> <td>Base Oil (VG32)</td> <td>98.9</td> </tr> <tr> <td>V0115</td> <td>0.8</td> </tr> <tr> <td>PPD</td> <td>0.3</td> </tr> </tbody> </table>			※Formulation		Base Oil (VG32)	98.9	V0115	0.8	PPD	0.3
※Formulation										
Base Oil (VG32)	98.9									
V0115	0.8									
PPD	0.3									
Kinematic Viscosity 100°C		10mm ² /s								

Polymer characteristics

Good SSI
 Good Pour point characteristics
 Easy handling by pellet form

Typical Applications

Viscosity Index Improver for lubricating oil

Physical Form

Polyethylene Bags; typical bag weight:25KG

Packaging

Loose bags, 14MT/20 feet container

Storage Conditions

Store in dry and well-ventilated place away from fire, sources of heat and direct sunlight.
 Avoid contamination and humidity.

Please consult the relevant safety data sheet for more detailed information.
 The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

For additional technical